



Light Gauge (LG)

APPLICATIONS -Suitable for Printing, Lamination process in flexible packaging applications.

Alloy Type -AA 1235/8079

TECHNICAL DATA SHEET							
Properties	Unit	Standard	Typical Values				
General							
Thickness	Micron	EN 546-3	8±0.4	9±0.45	11±0.55	12±0.6	
Width	MM	EN 546-3	<1000 ±0.1 and <1000±0.2				
Mechanical							
Tensile Strength	MPA	EN 546-2	Min. - 55 Max. - 100	Min. - 55 Max. - 100	Min. - 55 Max. - 100	Min. - 60 Max. - 110	
Elongation	%	EN 546-2	Min. - 1	Min. - 1	Min. - 1	Min. - 1	
Surface							
Pin Hole	Micro-holes / m ²	EN 546-4	100	50	20	20	
Wettability	Both Side	Dyne/cm	EN 546-4	"A" Grade	"A" Grade	"A" Grade	"A" Grade
Packing							
Seaworthy Export Standard Wooden Box Packing/Pallet Packing.							

Disclaimer: The data sheet information is to the best of our knowledge and experience. Some values may be customized wherever possible, as per the customer's requirement. Sparsh Industries Pvt. Ltd makes no warranty to the product fitness for any specific use. Data sheet is purely for reader's consideration and verification for sale or contract.

Sparsh Industries Pvt. Ltd.

Regd. Office:

Sparsh House, 165, Patparganj Industrial Area,
Delhi- 110092, INDIA
Tel: (+91) 11 42654646 / 42654747 Fax: (+91) 11 43086464

Factory Address:

Unit:2 – AH-01, NH-19, between Milestone 421-422,
Vill. Kumbhi, Akbarpur, Kanpur Dehat – 209101
Uttar Pradesh, INDIA

Email: info@sparshgroup.in

Website: www.sparshgroup.in



IMS + HACCP CERTIFIED